

Unipoly® X30 Grade

Technical Data Sheet

Unipoly® X30 Grade Expanded Polystyrene (EPS), is a rigid cellular plastic material that is strong, but has very low density. It is made in block and sheet form and is produced in Australia to meet Australian Standards, AS1366, Part 3. Unipoly® is tested against these minimum requirements.

Quality Assurance

Unipoly® X30 Grade exceeds the requirements of AS1366, Rigid cellular plastic sheets for thermal insulation Part 3: Rigid Cellular Polystyrene-Moulded.

Size and Shape

Unipoly® X30 Grade is produced in block form and sheet form to meet customer requirements. Standard sizes:

- 1.2 metre width
- 2.5, 3.0, 5.0, 6.0 metre lengths
- 20 mm up to 1.2 metre thickness

Other sizes and fabrications can be provided by Unipod® upon request.

Additional Information

Please consult Unipod® for design considerations and technical information on the full range of products available.

Physical Property	Test Method	Requirement/Result	Performance
Nominal Density	ISO 845	30 kg/m ³	N/A
Compressive strength at 1% deformation	AS 2498.3:1993	70 kPa	Pass
Cross Break Strength	AS 2498.4:1993	360 kPa (min)	Pass
k-Value (thermal conductivity) 50mm sample at 23°C	AS 4859.1: 2018	0.035W/mK (min)	N/A
R-Value (thermal resistance) 50mm sample at 23°C	AS 4859.1: 2018	1.43 m ² K/W (min)	N/A
Flame Propagation		2 SD (max)	Pass
Median flame duration			
Eighth value	AS 2122.1:1993	3 SD (max)	Pass
Median volume retained		50% (min)	Pass
Eighth value		47% (min)	Pass
Dimensional Stability – length, width, thickness	AS 2498.6:1993	1% (max)	Pass
Water Vapour Transmission, measured parallel to rise at 23°C	AS 2498.5:1993	400 µg/m ² s (max)	Pass
Elastic Modulus, min	ASTM D6817	7550 kPa	Pass